## **Product Bulletin**

## JPS-MTV

## 4.0 mil Matte White Vinyl

## Special "High Grip - High Bond" Adhesive

JPS-MTV 4.0 mil is specially formulated premium flexible matte white PVC film. This film has a unique "High Bond" acrylic pressure sensitive adhesive with a 90# layflat liner. The adhesive is formulated for the powersport graphic and decal markets. JPS-MTV can be printed on a variety of solvent-based, latex, UV and thermal printers that are commonly used in wide format. This product may also be printed on using other printing processes such as UV screen and UV curable offset but must be tested before production.

**Applications** 

**JPS-MTV** is designed for applications where a flexible premium film with special high bond adhesion is required. **JPS-MTV** is recommended for applications such as, Quads, Snowmobiles, Motocross, Powersport Vehicles, Helmets, and Carts. Testing is always suggested before application.

Recommended to use **JPS-MTL** 12mil Gloss Clear UV overlaminate.

This will add ultimate protection, performance and durability to the graphic or decal.

**Thickness** Film 4.0 mils.

Adhesive 1.8 to 2.2 mils. Liner 6.7 mils.

(Thickness variance +/- 10%)

Dimensional Stability

**Temperature Ranges** Minimum application temperature +40°F.

Service temperature -40°F to +180°F.

**Expected Exterior Exposure** 5 Years. Under normal exposure conditions

Adhesion To stainless steel 48 oz/in.

PSTC-101 Method A with 24 hr. dwell at 70°F and 50% relative humidity. Typical values. Individual values may vary. Test thoroughly before production.

Water Resistance Excellent Humidity Resistance Excellent Solvent Resistance Excellent

Storage Stability Six months shelf life when stored at 70°F and 50% relative humidity.

Product Codes JPS-MTV-15P (15" x 150' roll) "P" Indicates Gerber punched pattern

JPS-MTV-24 (24" x 150' roll) JPS-MTV-30 (30" x 150' roll) JPS-MTV-54 (54" x 150' roll) JPS-MTV-60 (60" x 150" roll)

Recommendations

Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation. Always thoroughly test this product to confirm that it meets your requirements. Proper surface preparation requires cleaning with alcohol or acetone to clean and remove contaminates before application. Failure to prepare the surface can cause premature failure of the graphic or decal.

<sup>\*</sup> JPS-MTV is a permanent adhesive system. Removing and repositioning are not characteristics of this adhesive system. The above recommendations of this films use do not suggest or constitute a verbal or written guaranty or warranty by the manufacture or its dealers of this product. Individual purchasers or users shall be responsible for determining the materials suitability as well as its intended use and application.



1313 boul. Dagenais ouest ● Laval, Quebec, Canada H7L 5Z9 ● (450) 622-6066 ● (866) 622-6066 ● FAX (450) 622-4537

Web Site: www.mediatech.ca • e-mail: info@mediatech.ca