

ORAJET® 3751RA+PROSLIDE® WRAPPING CAST DIGITAL MEDIA WITH RAPIDAIR® TECHNOLOGY

Technical Datasheet
06/26
Page 1 of 3

Description

2.25-mil, cast PVC film with a low-initial-tack adhesive, white gloss surface. Optimized repositionability and air-egress technology.

Release Liner

88# PE-coated silicone paper featuring *RapidAir®* + *ProSlide®* technology to facilitate quicker, easier application

Adhesive

Grey, solvent polyacrylate, repositionable, low-initial-tack, removable with heat
Cleanly removes up to 4 years from most well-conditioned OEM automotive paint systems.

Film Construction

Cast PVC film with a low-initial-tack adhesive

Colors + Finish

Available in white with a gloss surface.

Durability

- 8 years (unprinted)
- Printed/Laminated:
 - Climate Zone 1, 6 years
 - Climate Zone 2, 4 years
 - Climate Zone 3, 2 years

Applications

For long-term vehicle wrap and spot graphic applications requiring a superior degree of printability and durability. The *ProSlide®* adhesive technology enables the installer to easily position the wrap film into place due to its optimized repositionability. The *RapidAir®* technology makes installations quicker and easier, by allowing air bubbles to easily escape underneath the film, especially for large format panel applications and spot graphics. Realize significant time savings when using ORAJET® films featuring *RapidAir®* with *ProSlide®* adhesive technology for vehicle and boat wrapping.

Pair with ORAGUARD® 290, 290GF, or 293 for automotive and boat wrap applications, or long-term general signage applications. Pair with ORAGUARD® 289F for exceptional long-term durability where a more rugged, self-healing over-laminate is required.

Recommended Laminates

- ORAGUARD® 290 (2 mil Cast PVC)
- ORAGUARD® 290F (Optically Clear, 2 mil Cast PVC)
- ORAGUARD® 293 (1 mil Cast PVC)
- ORAGUARD® 294 (1.5 mil Cast PVC)

Printability/Ink Compatibility

Latex, Solvent, Eco-Solvent, and UV Curable. [Click Here](#) to view ORAFOL ICC Profiles.

Splice Free Guarantee

Our Splice Free Guarantee assures you that every roll of ORAJET® digital print media is free from splices. If you identify a verifiable splice, we will promptly replace the roll at no cost and provide you with \$500 as a token of our commitment to your satisfaction and uninterrupted graphic production experience.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafol.com

ORAJET® 3751RA+PROSLIDE® WRAPPING CAST DIGITAL MEDIA WITH RAPIDAIR® TECHNOLOGY

Technical Datasheet

06/26

Page 2 of 3

Technical Data

Thickness (without liner and adhesive)	2.25-mil
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.004"
Temperature Resistance	Adhered to aluminum, -58°F to +212°F, no variation
Fire Behavior (DIN 75200) Fire Rating	Adhered to steel, self-extinguishing ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 4.1 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 120% Across: Min. 120%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	8 years (unprinted)
Minimum Application Temperature	50°F
Available Lengths Available Widths (in inches)	150' (50-yard) and 75' (25-yard) 30, 50, 54, 60
Recommended Laminates	ORAGUARD® Series 290, 290GF, 293, 294
Print Compatibility	Latex, Solvent, Eco-Solvent, UV Curable

For best results, utilize ORAFOL ICC profiles available at www.orafol.com and allow solvent-based inks to dry for at least 24 hours (48-72 hours preferred) at 70°F before cutting the graphic to the ink or applying a laminate.

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafol.com

ORAJET® 3751RA+PROSLIDE® WRAPPING CAST DIGITAL MEDIA WITH RAPIDAIR® TECHNOLOGY

Technical Datasheet

06/26

Page 3 of 3

IMPORTANT NOTICE

All ORAJET® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAJET® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAJET® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use.

All specifications are subject to change without prior notice.

WARNING – This product may expose you to chemicals which are known in the State of California to cause cancer and birth defects or other reproductive harm. For more information, go to – P65Warnings.ca.gov



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafol.com